# IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

IN RE APPLICATION OF

Sullivan

**FOR** 

**IMPROVED MULTI-LAYER** 

**GOLF BALL** 

SERIAL NO.

08/870,585

**FILED** 

June 6, 1997

**ART UNIT** 

3711

**EXAMINER** 

M. Graham

LAST OFFICE ACTION

September 28, 2000

ATTORNEY DOCKET NO.

P-3724-2-F1

(SLD 2 0035-3-3-1)

Cleveland, Ohio 44114-2518

# PRELIMINARY AMENDMENT

Assistant Commissioner for Patents

Washington D. C. 20231

Dear Sir:

Please amend the above-captioned application as follows:

CERTIFICATE OF EXPRESS MAIL

I hereby certify that this PRELIMINARY AMENDMENT is being deposited with the United States Postal Service by Express Mail Procedure in an envelope addressed to: Assistant Commissioner for Patents, Box Patent Application, Washington, D.C. 20231 on April 10, 2001

Express Mailing Label No. EL545793944US.

Christina R. Correll Christina R. Correll

### IN THE SPECIFICATION:

Please replace the paragraph starting on page 1, line 1 with the following rewritten paragraph:

--This application is a continuation of U.S. Application Serial No. 08/870,585, filed on June 6, 1997, which is a file wrapper continuing application of U.S. Application Serial No. 08/556,237, filed November 9, 1995, which is a continuation-in-part of U.S. Application Serial No. 08/542,793 filed on October 13, 1995, which is in turn a continuation-in-part of U.S. Application Serial No. 08/070,510 filed on June 1, 1993.--

## IN THE CLAIMS:

Please amend the present claims as follows:

- 2. (Amended) A golf ball according to claim 1, wherein the inner cover layer has a thickness of about 0.100 to about 0.010 inches and the outer cover layer has a thickness of about 0.010 to about 0.070 inches, the golf ball having the properties required by the U.S.G.A. and having an overall diameter of 1.680 inches or more.
- 3. (Amended) A golf ball according to claim 1 wherein the inner cover layer has a thickness of about 0.050 inches and the outer cover layer has a thickness of about 0.055 inches, the golf ball having the properties required by the U.S.G.A. and having an overall diameter of 1.680 inches or more.
  - 6. (Amended) A multi-layer golf ball comprising: a spherical core;

an inner cover layer molded over said spherical core to form a spherical intermediate ball, said inner cover layer comprising an ionomeric resin having no more than 16% by weight of an alpha, beta-unsaturated carboxylic acid and having a modulus of from about 15,000 to about 70,000 psi;

5

10

an outer cover layer molded over said spherical intermediate ball to form a multi-layer golf ball, the outer layer comprising a non-ionomeric elastomer selected from the group consisting of polyester elastomer, polyester, polyether polyurethane and polyester amide, said outer cover layer having a modulus in a range of about 1,000 to about 30,000 psi.

# **REMARKS**

Applicants respectfully request that the present amendments be entered. It is believed that the present amendments place the application in condition for allowance.

Respectfully Submitted,

FAY, SHARPE, FAGAN, MINNICH & McKEE, LLP

Richard M. Klein Reg. No. 33,000 Mark E. Bandy Reg. No. 35,788

1100 Superior Avenue, 7th Floor Cleveland, Ohio 44114-2518

(216) 861-5582

L IDBCIDATAIMRISLD20353 PLA

### VERSION WITH MARKINGS TO SHOW CHANGES MADE

## IN THE SPECIFICATION:

The paragraph starting on page 1, line 1 has been replaced with the following paragraph:

--This application is a continuation of U.S. Application Serial No. 08/870,585, filed on June 6, 1997, which is a file wrapper continuing application of U.S. Application Serial No. 08/556,237, filed November 9, 1995, which is a continuation-in-part of U.S. Application Serial No. 08/542,793 filed on October 13, 1995, which is in turn a continuation-in-part of U.S. Application Serial No. 08/070,510 filed on June 1, 1993.--

### IN THE CLAIMS:

The present claims have been amended as follows:

- 2. (Amended) A golf ball according to claim 1, wherein the inner cover layer has a thickness of about 0.100 to about 0.010 inches and the outer cover layer has a thickness of about 0.010 to about [0.70] <u>0.070</u> inches, the golf ball having the properties required by the <u>U.S.G.A.</u> and having an overall diameter of 1.680 inches or more.
- 3. (Amended) A golf ball according to claim 1 wherein the inner cover layer has a thickness of about 0.050 inches and the outer cover layer has a thickness of about 0.055 inches, the golf ball having the properties required by the U.S.G.A. and having an overall diameter of 1.680 inches or more.
  - [8.] <u>6.</u> (Amended) A multi-layer golf ball comprising: a spherical core;

an inner cover layer molded over said spherical core to form a spherical intermediate ball, said inner cover layer comprising an ionomeric resin having no more than 16% by weight of an alpha, beta-unsaturated carboxylic acid and having a modulus of from about 15,000 to about 70,000 psi;

an outer cover layer molded over said spherical intermediate ball to form a multi-layer golf ball, the outer layer comprising a non-ionomeric elastomer selected from the group consisting of polyester elastomer, polyester, polyether polyurethane and polyester amide, said outer cover layer having a modulus in a range of about 1,000 to about 30,000 psi.

10